RECO$_2$® TYPICAL PROPERTIES

Property	Result
Particle Size Distribution (PSD)	Pass
Moisture Content	7.20%
Plasticity Index	Non-Plastic
Water content OMC	11%
Max Dry Density	2.03 Mg/m^3
Los Angeles Coefficient (LA)	37
Determination of Frost Heave	4.5 mm
Magnesium Sulphate Value	16%
Water Soluble Sulphate Content as % SO3	0.02%
Water Soluble Sulphate Content % SO4	0.03%
pH	12.2
Sulphates SO4	3.10%
Particle density on an oven-dried basis - OD	2.33 Mg/m^3
Particle density on a saturated and surface-dried basis SSD	2.48 Mg/m^3
Apparent Particle density	2.76 Mg/m^3
Water absorption	6.8%
GWP figure A1-A3	-16.1kg/tCO$_2$e*

**Carbon dioxide removals associated with the M-LS product are managed through a carbon credit registry and are only available by separate negotiation.*